

Water blocking solution

TECHNICAL DATA

TECHNICAL DATA	CURRENT VALUES	TEST METHODS
Material		
Material	Polyamid, modified; lead- and cadmiumfree	n/a
Specific gravity	0.96 g/cm ³ max.	ASTM-D 792, A-I
Mechanical Viscosity	180°C approx. 10 Pas; 200°C approx. 3,5 Pas	IEC 60684-2
Thermal		
Cold bend test	does not break at -40°C	ASTM-D 2671 Meth. C
Continuous operating temperature	-40°C to 125°C	n/a
Storage temperature	30°C max	n/a
Chemical		
Water absorption	0.50%	DIN 53495
Properties of rubber layer		
Material	Synthetic rubber basis	n/a
Specific gravity	1.4 g/cm ³ max.	ASTM-D 792, A-I
Cold bend test	does not break at -55°C	ASTM-D 2671 Meth. C
Continuous operating temperature	-40°C to 125°C	n/a
Storage temperature	30°C max	n/a

FOR FURTHER INFORMATION, PLEASE CONTACT:

Americas: 800 422 6872

Canada: 800 845 6808

Asia Pacific: +86 512 82280099

Europe: +49 2226 9047 355

All information contained in this datasheet is believed to be reliable. We advise however that customers should separately evaluate the suitability of our products for their particular application. Shawcor gives no guarantees in respect to accuracy or sufficiency of the information presented and disclaim any liability regarding its use. Our responsibilities are only those listed in our Standard Terms and Conditions of Sale for these products. In no instance will we be liable for any eventual, indirect, or consequential damage or damages arising from the sale, resale, transfer, use or misuse of the product. Subject to modification.