

Medium wall crosslinked polyolefin tubing

TECHNICAL DATA

TECHNICAL DATA	CURRENT VALUES	TEST METHODS
Material		
Tensile Strength	2,100 psi (14.5 MPa)	ASTM D412, ISO 37
Elongation	600%	ASTM D412, ISO 37
Elongation after Heat Aging (168 hr at 150°C)	500%	ASTM D2671
Heat Shock (4 hr at 225°C)	No cracking or flowing	ASTM D2671
Longitudinal Change	+1%, -10%	ASTM D2671
Low Temperature Flexibility (4 hr at -55°C)	No cracking	ASTM D2671
Specific Gravity	1.1	ASTM D792
Hardness (Shore D)	50D	ASTM D2240
Electrical		
Dielectric Strength	500 V/mil (20 kV/mm)	ASTM D149
Dielectric Voltage Withstand (2500 V, 60 Hz, 1 min)	No beakdown, 24 kV 1 min., 15 kV 4 hr	UL 486D
Volume Resistivity	10 ¹⁶ ohm-cm	ASTM D257
Chemical		
Fluid Resistance	Good to excellent	MIL-DTL-23053/5
Fungus Resistance	No growth	ASTM G21
Copper Corrosion	No corrosion	ASTM D2671
Water Absorption	0.1%	ASTM D570
Adhesive		
Adhesive Lap Shear (1 in/min at 23°C)	125 psi (0.875 MPa)	ASTM D1002
Adhesive Softening Point	92°C ±5°C	ASTM E28
Adhesive Peel Strength (300 mm/min at 23°C) to steel, aluminum, PE	35 pli	ASTM D1000
Adhesive Peel Strength (300 mm/min at 23°C) to PVC	20 pli	ASTM D1000
Adhesive Blocking (30°C)	No blocking	ASTM D1146
Water Penetration	No penetration after 286 hr of continuous immersion	STM 706

FOR FURTHER INFORMATION, PLEASE CONTACT:

Americas: 800 422 6872

Canada: 800 845 6808

Asia Pacific: +86 512 82280099

Europe: +49 2226 9047 355

All information contained in this datasheet is believed to be reliable. We advise however that customers should separately evaluate the suitability of our products for their particular application. Shawcor gives no guarantees in respect to accuracy or sufficiency of the information presented and disclaim any liability regarding its use. Our responsibilities are only those listed in our Standard Terms and Conditions of Sale for these products. In no instance will we be liable for any eventual, indirect, or consequential damage or damages arising from the sale, resale, transfer, use or misuse of the product. Subject to modification.