

## Adhesive lined crosslinked polyolefin

TECHNICAL DATA: DERAY®-SPLICEMELT TRANSPARENT	CURRENT VALUES	TEST METHODS
<b>Material</b>		
Material	Polyolefin, modified; free of lead, chromium VI, mercury and cadmium	n/a
Adhesive	Polyamid, modified	n/a
Surface	smooth	n/a
Specific gravity	1.00 g/cm <sup>3</sup> max.	ASTM-D 792, A-I
Shrink ratio	4:1	n/a
Longitudinal shrinkage	-10% max.	ASTM-D 2671
<b>Mechanical</b>		
Tensile strength	15 MPa	IEC 60684-2
Elongation	400%	IEC 60684-2
Secant modulus	175 MPa max.	ASTM-D 882
<b>Thermal</b>		
Tensile strength after thermal ageing (168 h at 160°C)	14 MPa	IEC 811-1-2
Elongation after thermal ageing (168 h at 160°C)	400%	IEC 811-1-2
Long term ageing (3,000 h at 125°C)	no cracking of outer jacket	n/a
Tensile strength after thermal shock (4 h at 200°C)	15 MPa	IEC 811-1-2
Elongation after thermal shock (4 h at 200°C)	370%	IEC 811-1-2
Cold bend test	does not break at -40°C	ASTM-D 2671 Meth. C
Combustion behaviour	passed	FMVSS 302
Shrink temperature	125°C to 200°C	n/a
Storage temperature	50°C max.	n/a
Continuous operating temperature	-40°C to 125°C	IEC 216
<b>Chemical</b>		
Corrosive action	non-corrosive	ASTM-D 2671 Meth. A
Compatibility with copper	non-corrosive	ASTM-D 2671 Meth. B
Resistance against chemicals	good	n/a
Water absorption	0.55% max.	VDE 0473
<b>Electrical</b>		
Dielectric strength	20 kV/mm	VDE 0303 Part 2
Spec. volume resistivity	10 <sup>14</sup> Ω x cm	VDE 0303 Part 3

### FOR FURTHER INFORMATION, PLEASE CONTACT:

Americas: 800 422 6872    Canada: 800 845 6808    Asia Pacific: +86 512 82280099    Europe: +49 2226 9047 355

We advise that customers should separately evaluate the suitability of our products for their particular application. Our responsibilities are only those listed in our Standard Terms and Conditions of Sale for these products. Please ask for the latest version of this data sheet. Subject to modification without prior notice.