

Cold shrink end caps

TECHNICAL DATA

TECHNICAL DATA	CURRENT VALUES	TEST METHODS
Material		
Shore A hardness	42	ASTM D 2240
Tensile at 100 % Psi	0.7 Mpa - 104 Psi	ASTM D 412
Tensile at 300 % Psi	3 Mpa - 435 Psi	ASTM D 412
Tensile max. Psi	7.7 Mpa - 1118 Psi	ASTM D 412
Elongation at break %	743	ASTM D 412
Dielectric constant	3.6	ASTM D 150
Specific gravity g/cm ³	1.131	ASTM D 792
Tear resistance (Die C) pli	225	ASTM D 624
Moisture absorption, 7 days 90C - %	0.96	ASTM D 570

FOR FURTHER INFORMATION, PLEASE CONTACT:

Americas: 800 422 6872

Canada: 800 845 6808

Asia Pacific: +86 512 82280099

Europe: +49 2226 9047 355

All information contained in this datasheet is believed to be reliable. We advise however that customers should separately evaluate the suitability of our products for their particular application. Shawcor gives no guarantees in respect to accuracy or sufficiency of the information presented and disclaim any liability regarding its use. Our responsibilities are only those listed in our Standard Terms and Conditions of Sale for these products. In no instance will we be liable for any eventual, indirect, or consequential damage or damages arising from the sale, resale, transfer, use or misuse of the product. Subject to modification.