

Modified crosslinked elastomer

TECHNICAL DATA: DERAY®-V25 / V25 TW	CURRENT VALUES	TEST METHODS
Material		
Material	Elastomer, modified; free of lead and cadmium	n/a
Surface	smooth, matt	n/a
Specific gravity	1.5 g/cm ³ max.	ASTM-D 792, A-I
Shrink ratio	2:1	n/a
Longitudinal shrinkage	-10% max.	ASTM-D 2671
Mechanical		
Tensile strength	20 MPa	IEC 60684-2
Elongation	520%	IEC 60684-2
Secant modulus	30 MPa max.	ASTM-D 882
Thermal		
Tensile strength after thermal ageing (168 h at 160°C)	13 MPa	IEC 60684-2
Elongation after thermal ageing (168 h at 160°C)	220%	IEC 60684-2
Tensile strength after thermal shock (4 h at 215°C)	12 MPa	IEC 811-1-2
Elongation after thermal shock (4 h at 215°C)	300%	IEC 811-1-2
Cold bend test	does not break at -75°C	ASTM-D 2671 Meth. C
Combustion behaviour	selfextinguishing	UL 224
Shrink temperature	150°C min.	n/a
Storage temperature	50°C max.	n/a
Continuous operating temperature	-75°C to 150°C	IEC 216
Chemical		
Corrosive action	non-corrosive	ASTM-D 2671 Meth. A
Compatibility with copper	non-corrosive	ASTM-D 2671 Meth. B
Resistance against chemicals	good	n/a
Water absorption	1.10%	VDE 0473
Electrical		
Dielectric strength	22 kV/mm	VDE 0303 Part 2
Spec. volume resistivity	10 ¹² Ω x cm	VDE 0303 Part 3

FOR FURTHER INFORMATION, PLEASE CONTACT:

Americas: 800 422 6872 Canada: 800 845 6808 Asia Pacific: +86 512 82280099 Europe: +49 2226 9047 355

We advise that customers should separately evaluate the suitability of our products for their particular application. Our responsibilities are only those listed in our Standard Terms and Conditions of Sale for these products. Please ask for the latest version of this data sheet. Subject to modification without prior notice.