

Heavy wall crosslinked polyolefin

TECHNICAL DATA

TECHNICAL DATA	CURRENT VALUES	TEST METHODS
Material		
Material	PE, modified; lead and cadmium free	n/a
Surface	glossy	n/a
Specific gravity	1.1 g/cm ³ max.	IEC 60684-2
Shore D hardness	> 40	IEC 60684-2
Longitudinal shrinkage	-10% max.	IEC 60684-2
Shrink ratio	3:1	IEC 60684-2
Mechanical		
Tensile strength	> 14.5 MPa	IEC 60684-2
Elongation	550%	IEC 60684-2
Thermal		
Tensile strength after thermal ageing (168 hrs at 150°C)	12 MPa	IEC 60684-2
Elongation after thermal ageing (168 hrs at 150°C)	500%	IEC 60684-2
Brittleness temperature	-55°C	IEC 60684-2
Combustion behaviour	passed	MVSS 302
Shrink temperature	120°C	DSG-Canusa internal
Storage temperature	40°C max.	IEC 60684-2
Continuous operating temperature	-55°C to 110°C	IEC 216
Chemical		
Tensile strength after immersion in oil & gasoline (24h at 23°C)	> 10 MPa	IEC 60684-2
Elongation after immersion in oil & gasoline (24h at 23°C)	> 300 %	IEC 60684-2
Water absorption	< 0.2 %	n/a
Electrical		
Dielectric strength	> 20 kV/mm	IEC 60684-2
Volume resistivity	10 ¹⁶ Ω x cm	IEC 60684-2
Properties of adhesive: Hotmelt EVA		
Softening point	100°C	ISO 11357-3
Low temperature flexibility	-20°C	IEC 60684-2
Corrosion	non-corrosive	IEC 60684-2

FOR FURTHER INFORMATION, PLEASE CONTACT:

Americas: 800 422 6872 Canada: 800 845 6808 Asia Pacific: +86 512 82280099 Europe: +49 2226 9047 355

We advise that customers should separately evaluate the suitability of our products for their particular application. Our responsibilities are only those listed in our Standard Terms and Conditions of Sale for these products. Please ask for the latest version of this data sheet. Subject to modification without prior notice.